



Ficha Técnica do Produto
Fiche Technique du Produit
Product's Technical File

OURIQUE



Composição : 70% ALGODÃO | 10% LINHO | 20% ACR | Composition : 70% COTTON | 10% LINEN | 20% ACR |
Composition : 70% COTON | 10% LIN | 20% ACR

	Unidade Unité Unit	Método Méthode Method	Resultado Spécifications Results
Peso total Masse du tissu Total weight	g/ml		645
Peso total Masse du tissu Total weight	g/m ²		430
Comprimento do rolo Roll length Longueur du rouleau	m		30
Largura Largeur Width	m		1,50
Solidez da cor à luz Tenue à la lumière Colour Fastness	Grau Degré Grade	ISO 105-B02:2014	4/5
Solidez à fricção Solidité au frottement Resistance to rubbing	Grau Degré Grade	UNE-EN ISO 105-X12:2003	Seco 5 Húmido 5 À sec 5 Au mouillé 5 Dry 5 Wet 5
Resistência à abrasão Résistance à l'abrasion Abrasion resistance	Ciclos Cycle Cycle	Martindale 12 kPa ISO 12947-2:1998 + TC1:2002	> 50.000
Classe Ignífuga Classement de feu Fire proof norm		UNE EN 1021-1:2006 (cigarro)	OK
Classe Ignífuga Classement de feu Fire proof norm		IMO 2010 FTP CODE	OK
Absorção Acústica Absorption Acoustique Acoustic Absorption		UNI EN ISO 354:2003	OK

Tratamento COEX® ignífugo / antibacteriano / hidro-óleo repelente disponível (100% natural)
COEX® Fireproof / anti-bacterial / hydro-oil repellent available (100% natural)
Traitement COEX® anti-feu / antibactérien / hydro-oléofuge disponible (100% naturel)

EN 1021-2 (chama | flame | flame)
DIN 4102 B1
NF P 92-503 to 92-505, 92-507 (M1)
BS 5852 (Crib 5, 7)
California TB 116, 117, 133

De lote para lote podem existir variações de cor dentro dos limites toleráveis.
Des variations tolérables de coloris d'un bain à un autre peuvent se manifester.
Batch to batch variations may occur within commercial tolerances.

www.carlosnatal.pt